

Technical Data

PERMAGUARD FILLER M.E.



Product description

Permaguard Filler M.E. is a two pack solvent free epoxy filler.

Recommended use

For use on concrete, blockwork, plaster, steel and other materials where a filler is required to level the surface and fill cracks prior to overcoating with suitable coating systems.

Permaguard Filler M.E. is suitable for use on interior and exterior surfaces of buildings, concrete and steel tanks.

Film thickness and spreading rate

	Minimum	Maximum
Film thickness, dry (μm)		2000
Film thickness, wet (μm)		2000
Theoretical spreading rate (m^2/l)		0.5

Physical properties

Colour	Grey
Solids (vol %)*	100 \pm
Flash point	N/A

*Measured according to ISO 3233:1998 (E)

Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

For steel substrate: The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. For Concrete: The moisture content in the concrete should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Application methods

Other Putty knife

Application data

Mixing ratio (volume) 1 part of component A (base) to be thoroughly mixed with 1 part of component B (hardener). The two components should be mixed by spatula and proper agitation kneading.

Pot life (23°C) 2 hours at 20°C, ½ hour at 35°C.

Thinner/Cleaner Jotun Thinner No. 17

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	10°C	23°C	40°C
Surface dry	30 h	15 h	5 h
Through dry	48 h	24 h	10 h
Cured	14 d	7 d	3 d
Dry to recoat, minimum	48 h	24 h	10 h

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Permaguard Filler M.E. can be used as a blowhole and crack filler on concrete plaster and steel prior to the application of suitable coating system.

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

2 Ltr. (comp. A) And 2 Ltr. (comp. B).

Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Head Office & Nordic

Jotun Paints
P.O. Box 2021
N-3248 Sandefjord
Norway
Phone +47 33 45 70 00
Fax +47 33 46 46 13

Europe

Jotun Paints (Europe) Ltd.
Stather Road, Flixborough
North Lincolnshire DN15 8RR
United Kingdom
Phone +44 172 44 00 000
Fax +44 172 44 00 100

Middle East

Jotun U.A.E Ltd. LLC.
Al Quoz Industrial Area
P.O Box 3671
Dubai U.A.E
Phone +971 4 3 39 50 00
Fax +971 4 3 38 06 66

South East Asia

Jotun (Singapore) Pte. Ltd.
No 11-15, Sixth Lok Yang
Road
Jurong
Singapore 628 111
Phone +65 6265 4711
Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 8 MAY 2002 BY JOTUN PAINTS
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED