

# Aquaprime-X

## Exterior Primer



Steel House, West Wharf Road, Karachi-74000, Pakistan. Tel: (92-21) 2856601 Fax: (92-21) 2856598

A quick drying high opacity water dilutable product based on special acrylic polymers. It may be used as both primer and undercoat in Exterior & Interior surfaces.

### USES

Designed for exterior use as both primer and undercoat on plaster, cement, brickwork, render, building boards etc., or use as a sealer coat on previously painted surfaces.

### PROPERTIES

#### Appearance

Flat

#### Volume Solids

66% ± 2

#### Colour

Brilliant White

#### Pack Size

5 liters and 16 liters

#### Spreading Rate

10 – 14 Sq. Mt. /liter depending on surface texture, porosity and application method.

#### Drying Time

Surface dry in 1 hour. Re-coatable after 3 hours (in normal drying conditions).

#### Flash Point

Not Applicable

#### Shelf Life

2" Years when stored in dry and cool conditions.

### APPLICATION DATA

Stir well before use. Apply by brush, roller, air spray or airless spray. For details of spray equipment, contact PATSA Technical Services Department.

#### Thinning

Brush and Roller 5% sweet water.

Air Spray and Airless Spray 10% sweet water.

#### Cleaning

Clean all tools and equipment immediately after use with clean water.

#### Caution

Do not use when humidity levels may cause surface Condensation (maximum 85%), during rainy conditions or if temperatures are likely to fall below 5°C during application and drying. Protect from frost.

### SPECIFICATION

#### Preparation (New Work)

##### All Surfaces Interior

All surfaces should be sound, clean, dry and free from loose and flaking material, dirt, efflorescence oil, grease, wax, polish etc.

##### All Surface Exterior

All surfaces should be sound, clean, dry and free from loose and flaking material, dirt, efflorescence oil, grease, wax, polish etc. Apply AQUAPRIME-X & allow to dry. Fill small cracks and surface imperfections with suitable wallfiller; larger cracks may be filled with Asocret RN.

#### Preparation (Previously Decorated)

All surfaces should be sound, clean, dry and free from loose and flaking material, dirt, efflorescence oil, grease, wax, polish etc. Where necessary spot prime with the AQUAPRIME-X, and where appropriate fill small cracks and surface imperfections with suitable wallfiller; larger cracks may be filled with Asocret RN.

[See Note \[i\]](#)

#### Decoration (New and Previously Decorated)

##### All Surfaces

Apply one coat of PATSA AQUAPRIME-X.

See Note [i, ii, iii, iv]

# Aquaprime-X

Exterior Primer



Steel House, West Wharf Road, Karachi-74000, Pakistan. Tel: (92-21) 2856601 Fax: (92-21) 2856598

## NOTES

- i. Alkyd based and gloss painted surfaces should be thoroughly washed and rubbed down before painting.
- ii. Surfaces of high porosity (very chalky and powdery) should be primed with one coat of AQUAPRIME-X diluted 10% with sweet water.
- iii. Two coats of Aquashield Silk or Aquasilk will be required on external surfaces if AQUAPRIME-X is to be used as primer and undercoat.
- iv. It is recommended to over coat AQUAPRIME-X within 7 days of application with suitable finish coat

## SAFETY INFORMATION

Use only in well ventilated areas. In case of insufficient ventilation during spraying, wear suitable respiratory equipment. Do not breath vapor / spray.

In case of contact with eyes, rinse immediately with plenty of sweet water and seek medical advice. Keep out of reach of children