

PATSA RED OXIDE

RUST PREVENTING PRIMER

PRODUCT DESCRIPTION:

Patsa Red Oxide is a primer based on alkyd resin with active rust inhibiting inorganic pigments. The primer has high adhesion strength and is ideal for long term rust prevention on all types of steel structures.

Advantages:

- Good anti corrosive properties
- Excellent adhesion to metal surfaces
- Good flexibility
- Good hiding capacity
- Ideal for interior and exterior surfaces

PROPERTIES:

Color	: Red
Coverage	: 13 – 15 m ² / lit.
Flash Point	: 39°C
Solid Content	: 54% ± 2%
Recommended	: 35 µ / coat

Drying Time

Touch Dry	: After 2 hrs
Over coating	: Min 12 hrs

APPLICATION PROCEDURE:

- Substrate must be free from rust, dirt, oil, grease and other contaminants.
- Remove all loose, peeling, or chalky paint by sanding, scraping, high-pressure washing, sand-blasting or other appropriate methods.
- Method of Application:
By brush, roller and Conventional Spray

SPRAY DATA:

Conventional Spray

Nozzle Orifice	: 2 – 3mm
Nozzle Pressure	: 43 – 57 psi
Dilution	: 10 – 15 %
Thinner	: # 2

Cleaning of Tools

All tools should be cleaned with Thinner no. 2

STORAGE:

Patsa Red Oxide should be kept in a cool area below 25°C. Keep in tightly closed container.

SHELF LIFE:

One: (1) year in cool place.

PACKING:

Available in 5 lit, 20 lit. (Drum)

MATERIAL SAFETY:

Patsa Red Oxide does not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. Patsa Red Oxide is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advice.

Disclaimer: The information and recommendations above are given in good faith based on our current knowledge and experience of the products when properly stored, handled and applied in accordance with current best practice, national standards and our recommendations. As we have no control over site conditions or methods of application, no liability can be derived from the contents of this information sheet, or from any written recommendations, or from any other advice offered. The user of the product is solely responsible for the product's suitability for the intended application and is recommended to test the suitability prior to use. We reserve the right to change the properties of our products without notice. All orders are sold subject to our current terms of sale and delivery. With the publication of this Technical Information Sheet all previous edition are no longer valid.

Issued March 2016