

ROAD MARKING PAINT

BASED ON METHACRYLATE RESIN MEETING FAA STANDARDS

PRODUCT DESCRIPTION:

A quick drying, 100% Acrylic solvent based, high build Road Marking Paint, which has good resistance to wear and tear, impact, oil, gasoline and water. To enhance the reflective properties of the paint glass beads may be incorporated by either premixing (2 parts paint: 1 paint beads) or by dropping into the surface of the wet paint. The first method gives long term reflection as traffic abrasion continually exposes the spheres; whilst the second gives immediate reflection but this declines with continued wear. buyer, hereby expressly waives any claim to additional damages.

RECOMMENDED USES

Suitable for interior or exterior use for the lining/ marking of roads runways, pavements, car parks, playgrounds, warehouses, safety areas. Typical substrates include concrete, stone, and asphalt.

PRODUCT CHARACTERISTICS

Appearance : Bright
Volume of Solids: 72% ± 2%
Color Range : White, Yellow and Black.
Pack Size : 5 liters and 20 liters.

Spreading Rate:

Up to 14.4 sq. mtr. / Liter at 50 DFT per coat, depending on surface texture, thickness and method of application.

Recommended thickness 100 microns for the complete coating system.

Drying Time:

Surface dry in 15 minutes. Re coatable after 6 hours in normal drying conditions.

Shelf Life:

1 Year when stored in dry and cool conditions

APPLICATION CONDITIONS

Stir well before use. Apply by brush, roller, air spray or specially modified airless spray. (For details of spray equipment, contact PATSA Technical Service Department.

Thinning:

Brush / Roller 0 – 5% PATSA Thinner 7.

Air / Airless Spray 0 – 15% PATSA Thinner 7.

Cleaning:

Clean all tools and equipment immediately after use with PATSA Thinner 7.

Caution:

Do not use when humidity levels may cause surface condensation (maximum 85%), during rainy conditions, or if temperatures are likely to fall below 5°C during application and drying. Protect from frost.

SURFACE PREPARATION

Preparation (New and Previously Decorated Surfaces) All Surfaces All surfaces should be sound, clean, dry and free from loose and flaking materials, efflorescence, laitance, curing compounds, dirt, oil, grease etc. See notes [i, ii, iii]

Decoration (New and Previously Decorated Surfaces)

All Surfaces Apply one or two coats of PATSA Road Marking Paint. See notes [iv, v]

SAFETY - FLAMMABLE

Use only in well-ventilated areas. In case of insufficient ventilation during application, wear suitable respiratory equipment. Do not breathe vapor / spray. In case of contact with eyes rise immediately with plenty of sweet water and seek medical assistance.

ROAD MARKING PAINT

BASED ON METHACRYLATE RESIN MEETING FAA STANDARDS

NOTES

- i. Remove oil, grease and other surface contaminants by thoroughly washing with an industrial detergent such as Glo- Flo H.D. Degreaser. (Rinse with clean water and allow to dry before coating).
- ii. Laitance – A hard, brittle, loosely bound “skin” formed on the surface of concrete during drying must be removed for effective long-term adhesion. Remove either by chemical means e.g. acid etching, or by mechanical means e.g. abrasive blasting, or high pressure water jetting. (For more details of preparation methods contact PATSA Technical Services Department)
- iii. The concrete must be fully cured (at least 4 weeks old) and basement or ground level floors must include a damp proof membrane, otherwise rising damp may cause the blistering / disruption of any paint applied. Asphalt must have aged for at least six months (if less than six months old contact PATSA Technical Services Department).
- iv. Roller or brush application is not recommended on Asphalt-based surfaces.
- v. Do not brush second coat excessively as the solvents may cause softening and pick-up of the first coat.

WARRANTY

PATSA Company warrants the products to be free of manufacturing defects in accord with applicable quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by our technical team. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY PATSA, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Disclaimer: The information and recommendations above are given in good faith based on our current knowledge and experience of the products when properly stored, handled and applied in accordance with current best practice, national standards and our recommendations. As we have no control over site conditions or methods of application, no liability can be derived from the contents of this information sheet, or from any written recommendations, or from any other advice offered. The user of the product is solely responsible for the product's suitability for the intended application and is recommended to test the suitability prior to use. We reserve the right to change the properties of our products without notice. All orders are sold subject to our current terms of sale and delivery. With the publication of this Technical Information Sheet all previous editions are no longer valid.

Issued March 2016